

ETHYLENE VINYL ACETATE - EVA

	UNEXEVAT1	UNEXEVAT2	UNEXEVAT4	UNEXEVAT6
Melting range (Kofler - °C)	68-80	70-85	60-76	68-82
Melting point (DSC - °C)	69	72	69	62
Melt flow index (g/10min at 190°C/2,16kg)	150	20	400	20
Hardness (Shore)		73A	71A	73A
Laundry up to (°C)	30	40	30	45
VA (FT - IR - %)	28	28		33
Particle size (µm)	0-200 200-400	0-200 200-400	200-400	200-400

Values are not for use as specification, but are typical values

OUR EVA RANGE

- Cost effective adhesive resin
- Excellent adhesion to many substrates
- Anti-slip properties
- Wide viscosity range



DAKOTA
POWDER ADHESIVES